CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-11-27-09** **Date: 30-11-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at balance main and cross roads at Manavarthi Thota, Chowdeshwari Layout areas in ward No.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (West), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/162/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	27-11-17
Sample ID No	:	2017-11-27-09/02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	27-11-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	322	322	2.1	97.9	90-100
3	20 mm	5643	5965	39.8	60.2	30-70
4	10 mm	4663	10628	70.9	29.1	10-35
5	4.75 mm	4025	14653	97.7	2.3	0-5
6	Pan	347	15000	100.0	0	---

AE-2

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-11-27-09** **Date: 30-11-17**

Sample ID No : 2017-11-27-09/02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.6	
3	Specific Gravity	2.68	–
4	Bulk Density(Loose) (Kg/l)	1.55	–
5	Bulk Density(Compacted) (Kg/l)	1.59	–
6	Water Absorption(%)	0.21	–

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE-2

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2017-11-27-09** **Date: 30-11-17**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drain at balance main and cross roads at Manavarthi Thota, Chowdeshwari Layout areas in ward No.02 of Yelahanka Sub Division.

Agency : Technical Manager (West), KRIDL, BBMP, Bangalore.

Customer's Reference : BBMP/EE(YNK.D)/W.O/162/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-11-17

Sample ID No : 2017-11-27-09/02(b)

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 27-11-17

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	86	86	8.6	91.4	90-100	90-100	90-100	95-100
3	2.36 mm	144	230	23.0	77.0	60-95	75-100	85-100	95-100
4	1.18 mm	175	405	40.5	59.5	30-70	55-90	75-100	90-100
5	600 micron	179	584	58.4	41.6	15-34	35-59	60-79	80-100
6	300 micron	185	769	76.9	23.1	5-20	8-30	12-40	15-50
7	150 micron	132	901	90.1	9.9	0-10	0-10	0-10	0-15
8	Pan	99	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

AE-2

CIVIL PRO Sig..... Date..... BANGALORE

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : **CP-2017-11-27-09**

Date: 30-11-17

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drain at balance main and cross roads at Manavarthi Thota, Chowdeshwari Layout areas in ward No.02 of Yelahanka Sub Division.

Agency : Technical Manager (West), KRIDL, BBMP, Bangalore.

Customer's Reference : BBMP/EE(YNK.D)/W.O/162/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-11-17

Sample ID No : 2017-11-27-09/01

Sample Type : ACC 53grade

Reference to BIS codes : IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 (Part 1,2 3,4,5, 6,11):1988
IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4
IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5
IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5
IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6

Date of test : 28-11-17

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.55	–
2	Finess by Air permeablity method (m^2/kg, Min)	275.5	225m^2/kg, Min
3	Density (gm/cc)	3.11	–
4	Standard Consistency (%)	27.0%	Not specified
5	Initial Setting time	165 minutes	Not less than 30 minutes
6	Final Setting time	255 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2.0mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Yelahanka Sub Division
(BBMP Ynk. Zn.)
Yelahanka, Bangalore

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****